

Passion Art Coaster Composition

Composition	Percentage
WHITE CLAY	28%
PYROPHYLLITE	25%
KAOLIN	15%
TALCUM POWDER	12%
WOLLASTINITE	8%
CHAMOTTE	7%
OTHER	5%

Kiln Temperature: 1100 centigrade