

Doc Ref: FCS 2004-1a

## **RECTALEEN SPECIFICATION SHEET**

## 350mym STATIONERY - DOTP

FLEXIBLE PENDLE EMBOSSED PLAIN PVC

Thickness (mym) 350 +/- 5% Plasticise r DOTP

Handle (phr) 41 +/- 1 (DOTP)

Cold Crack (°C) -7 max NEN-EN-ISO 8570

**General Properties** 

Formulated to conform to: EC No: 1907/2006 (REACH), NEN-EN 71-3, NEN-EN 71-9, EU94/62/EC packaging, EU 202/95/EC (RoSH)

DOES NOT CONTAIN:

 $\label{eq:discontinuity} DEHP-di-ethylhexyl\ phthalate,\ DBP-Dibutyl\ phthalate,\ BBP-benzyl\ butyl\ phthalate,\ DINP-di-isononyl\ phthalate,\ DIDP-di-isononyl\ phthalate,\ DIOP-di-isononyl\ phthalate,\ DIOP-di-iso$ 

European Guideline 2002/95/EC(RoHS) and are free of Cadmium, Lead, Lead Chromate, Mercury, PBB & PBDE categories

**Physical Properties** 

TENSILE STRENGTH - 19MPa BS EN ISO 527-3

**ELONGATION AT BREAK - 190%** 

TEAR STRENGTH - 140N/mm DIN 53363

DIMENSIONAL STABILITY - 1.5%max 5min/70 C

Possible End Use

Textured PVC, for Stationery Products- Binders, Folders and also suitable for use in children's products

Available from stock in a range of colours. Slitting, Guillotine, Pressing, Converting Service also available

## CONTACT SALES OR TECHNICAL DEPARTMENT IN CASE OF QUERIES

All above information shall only be used as a guide; buyers shall independently test and determine the products suitability.

The mentioned data are average of test results and should not be used for the purpose of lawsuit or warranty.

e-mail: sales@flexr.co.uk Telephone: 01282 478222 Fax: 01282 478210 Website: www.flexr.co.uk

QA70 D004 Issue Date: 13/04/2017 Issue No: 2

