

TECHNICAL DATA ▶

Physical Properties			Indoor Decorative	Outdoor Durable
Test Method				
Finish			Various - See Chart	Various - See Chart
Color			Various - See Chart	Various - See Chart
Adhesive			High Peel, High Tack Permanent, P102	High Peel, High Tack Permanent, P102
Film			Metallized Flexible Vinyl	Metallized Flexible Vinyl
Liner			88# Layflat Liner	88# Layflat Liner
Opacity			2.2 minimum	2.2 minimum
Thickness	Film	TAPPI T-411	3.0 ± 0.3 (76 ± 8)	3.0 ± 0.3 (76 ± 8)
	Film + Adhesive	TAPPI T-411	3.7 ± 0.5 (94 ± 13)	3.9 ± 0.5 (94 ± 13)
	Total Thickness	TAPPI T-411	10.1 ± 0.6 (259 ± 15)	10.3 ± 0.6 (262 ± 15)
Adhesion to Stainless Steel	15 Minutes	ASTM D3330	40 oz/in typical	40 oz/in typical
	24 Hours	ASTM D3330	60 oz/in typical	60 oz/in typical
Weight	Film + Adhesive	TAPPI T-410	123 - 138 gsm	126 - 141 gsm
	Total w/ Liner	TAPPI T-410	260 - 285 gsm	265 - 290 gsm

Conditions for Use			Indoor Decorative	Outdoor Durable
Shelf Life			1 year	1 year
Outdoor Durability			Indoor use only	Up to 3 years
Min Application Temp			40° F (4° C)	40° F (4° C)
Service Temp Range			-20° to 130° F (-29° to 55° C)	-20° to 130° F (-29° to 55° C)
Solvent Resistance			Good	Good
Water Resistance			Good	Good

The information provided herein is correct to the best of Nekoosa's knowledge. No liability for any errors, facts or opinions are accepted. Customers must satisfy themselves as to the suitability of this product for their application. No responsibility for any loss as a result of any person placing reliance on any material contained herein will be accepted.